迪森纸® Dawnsens® H1060
Technical Description Sheet 主要规格特性

Property 项目	Units 单位	Test Method 测试标准	Typical value 典型值
Basis Weight 基本重量	g/m^2	GB/T 451.2-2002	62
Thickness 厚度	mm	GB/T 451.3-2002	0.15
Tensile Strength, MD 纵向抗张强度	kN/m	GB/T 12914-2018	5.0
Tensile Strength, CD 横向抗张强度	kN/m	GB/T 12914-2018	4.1
Elongation, MD 纵向断裂伸长率	%	GB/T 12914-2018	21
Elongation, CD 横向断裂伸长率	%	GB/T 12914-2018	50
Elmendorf Tear, MD 纵向撕裂度	N	GB/T 455-2002	2.7
Elmendorf Tear, CD 横向撕裂度	N	GB/T 455-2002	2.6
Mullen Burst 耐破度	kPa	GB/T 454-2002	680
Air Permeability 透气度	μm/(Pa.s)	GB/T 458-2008	22
D65 Brightness D65 亮度	%	GB/T 7974-2013	87
Hydrostatic Head 静水压	Pa	GB/T 4744-2013	19000
Moisture Vapor Transmission 透湿量	$g/(m^2.24h)$	GB/T 1037-2021	3000

迪森纸® 材料科技 Dawsens® Material Technology

表格信息是基于当盛新材认为可靠的技术数据，这些信息将会不定期更新，当盛新材不保证与这些信息相关的试验结果，不承担以此发生的任何义务或责任。

当盛®、当盛 D 形标志，迪森纸®等商标和服务标识均归当盛新材及其关联公司所有。

The information in this form is based on the technical data Dangs considers reliable. The data may be updated without prior notice as additional knowledge are gained. Dangs makes no guarantee of these results and does not assume any obligation or liability in connection with this information.

当盛®, D logo, Dawnsens® and other trademarks and service marks are owned by Xiamen Dangs New-Materials Co.,LTD. and its affiliates.