当盛® Dawnsens® DSX1050
Technical Description Sheet 主要规格特性

Property 项目	Units 单位	Test Method 测试标准	Typical value 典型值
Basis Weight 基本重量	g/m^2	ISO 536:1995	51
Thickness 厚度	mm	ISO 534:1988	0.14
Tensile Strength, MD 纵向抗张强度	kN/m	ISO 1924-2:2008	2.2
Tensile Strength, CD 横向抗张强度	kN/m	ISO 1924-2:2008	2.4
Elongation, MD 纵向断裂伸长率	%	ISO 1924-2:2008	18
Elongation, CD 横向断裂伸长率	%	ISO 1924-2:2008	44
Elmendorf Tear, MD 纵向撕裂度	N	ISO 1974:1990	4.0
Elmendorf Tear, CD 横向撕裂度	N	ISO 1974:1990	3.9
Mullen Burst 耐破度	kPa	ISO 2758:2001	450
D65 Brightness D65 亮度	%	ISO 2470-2:2008	89

*本材料组成为 HDPE，阻燃等级为具有一定可燃性，使用时需避免明火及火花，并注意施工安全。

当盛® 材料科技 Dawnsens® Material Technology

表格信息是基于当盛®认为可靠的技术数据，这些信息将会不定期更新，当盛®不保证与这些信息相关的试验结果，不承担以此发生的任何义务或责任。

当盛®、当盛 D 形标志，Dawnsens®等商标和服务标识均归当盛®及其关联公司所有。

The information in this form is based on the technical data Dawnsens® considers reliable. The data may be updated without prior notice as additional knowledge are gained. Dawnsens® makes no guarantee of these results and does not assume any obligation or liability in connection with this information.

当盛®, D logo, Dawnsens® and other trademarks and service marks are owned by Dawnsens New Materials (Xiamen) Co.,LTD. and its affiliates.